

Properties

B5723

Glass fiber-reinforced flame retardant PBT/ABS resin (GF15%, UL94 V-0)

Heat resistance

Properties	Test methods	Test conditions	Units	
Mold shrinkage	ASTM D955	-	%	0.4-0.6
Tensile strength	ISO 527	-	MPa	91
Flexural strength	ISO 178	-	MPa	130
Flexural modulus	ISO 178	-	MPa	5600
Notched Charpy impact strength	ISO 179/1eA	23 deg C	kJ/m2	6
Notched Izod impact strength	ASTM D256	23 deg C/6.4mm	J/m	60
Deflection temperature under load	ISO 75	1.80MPa	deg C	175
Deflection temperature under load	ASTM D648	1.82MPa/6.4mm	deg C	185
Deflection temperature under load	ISO 75	0.45MPa	deg C	210
Deflection temperature under load	ASTM D648	0.46MPa/6.4mm	deg C	210
Coefficient of linear thermal expansion	ISO 11359	MD	X1E-5/deg C	3
Coefficient of linear thermal expansion	ISO 11359	TD	X1E-5/deg C	10
Flammability	UL94	-	-	V-0/1.5mm
Dielectric strength	ASTM D149	1.5mm	MV/m	29
Arc resistance	ASTM D495	3.0mm	sec(PLC)	-(6)
Hot wire ignition	UL746A	1.5mm	sec(PLC)	27(3)
High ampere arc ignition	UL746A	1.5mm	(PLC)	25(3)
High voltage tracking rate	UL746A	3.0mm	mm/min(PLC)	87(3)
Comparative tracking index	IEC 112	3.0mm	V(PLC)	225(3)
Water absorption	ISO 62	-	%	0.15
Density	ISO 1183	-	g/cm3	1.43

Note

- Values are typical, not quality assured.
- UL recognition File No. of Daicel Polymer is E47773.

Typical settings for processing

Preliminary drying	Barrel temperature(deg C)				Screw rotation (rpm)	Back pressure (MPa)	Mold temperature (deg C)
	Nozzle	Front	Middle	Back			
3-5hrs 80-120deg C	230-250	240-250	220-240	190-230	50-90	5-20	60-80